



Product Data Sheet

Product Number: F-716Y Golden Glue EXTERIOR

Description: Type II Adhesive

F716Y is a pre-catalyzed crosslinking adhesive for exterior grade applications. It can also be used for Radio Frequency bonding and Hot Press Applications. Final bonds of F716Y are water resistant, and will conform to D3/Type 2 specifications.

Benefits:

Exterior Grade Wood Glue
Passes ANSI TYPE 11 Water Resistance
Hot or Cold Press
Fast Set
RF Gluing
Easily Sandable
OTC Compliant
Cal SCAQMD Compliant

Typical Physical Properties:

Solids:	49% +/- 3%	Open Time:	Approx. 5 minutes
Viscosity:	4400 cps	Closed Time:	Approx. 20 minutes
Color:	Yellow	Press Time:	Approx. 30 - 45 minutes @ 40psi
Coverage:	240 sq ft/gal	VOC:	18.09 g/l (EPA Method 24)
Coverage Rate:	6 – 9 wet mls	Shelf Life:	One year in unopened container
		Chalk Temperature:	55°F
		Packaging:	1, 5, 55, and 275 gal container

Qualifies for Leed Points 3.2, 4.1 and 4.4

Application Instructions:

Hot or Cold Press

1. Apply adhesive via Black Brothers A2158 roll coater (glue spreader). For best results use dual durometer rollers to insure thorough coverage.
2. Apply 6 – 9 wet mls onto the board surface.
3. Working time of the adhesive is 5 – 7 minutes and closed time to move the stack is 15 – 20 minutes. For cold press operations, 1- 2 hours of press time at 40 – 50 psi is recommended. Delay machining for 8 – 12 hours once out of press.
4. For hot press applications, set temperature at 180 – 200° F with dwell of 69 – 90 seconds. Wait 15 minutes after substrate has cooled for machining.

FORMICA is a registered trademark of the Formica Corporation

NOTICE TO PURCHASER: The information, data and suggestions for use of the materials given here are based on our best experience and knowledge, but we do not guarantee the results to be obtained in customer's processes. The products discussed are sold without any warranty regarding merchantability or fitness for a particular purpose or any other warranty express or implied. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Since the manufacturer of the described in this data sheet has no means of controlling the final use of the product by the consumer or user, it is the responsibility of the immediate purchaser and any intermediate sellers to inform the user of the purposes for which the product may be fit and suitable, and of the properties of the product, including the precautionary measures which must be taken in order to insure the safety of the user and of other third persons and property.

2014-05



666 Redna Terrace, Suite 600
Cincinnati, OH 45215
Customer Service: (800) 330-5566

Assembly

1. Apply 6 mls (or at rate of 240 sq ft/gal) via glue spreader, brush/roller or squeeze bottle.
2. The joint have been prepped to fit together snugly.
3. Open time to bring the glue joint together is 5 - 8 minutes.
4. Apply pressure to the bondline with pressure recommendations being 100 – 150 psi for soft woods, 125 – 200 for medium density woods and 150 – 250 psi for hardwoods.

Substrates to Avoid:

Moisture Resistant Boards
Tempered Hardwood Products
Metallized, polyester or painted surfaces
Low Pressure melamine
Fire retardant treated board

Limitations:

Not for structural or load bearing applications. Do not use when temperature, glue or materials are below 55°F. Freezing may not affect the function of the product but may cause it to thicken. Agitation should restore product to original form. F716Y is not intended for use under conditions submersion or applications below the water line.

Clean Up:

Warm soapy water while adhesive is still wet
Used diluted ammonia to clean dried adhesive
Washer water is NRCA non-hazardous

Storage Conditions:

Do not subject to freezing conditions
Insure adhesive and substrates are conditioned above 65°F.
Best results are achieved between 70 and 85°F.

Precautions:

For consumer or professional use.
Keep out of reach of children.
Do not store in direct sunlight.

Please refer to the Material Safety Data Sheet for further safety information